



**EUROPEAN PATENT APPLICATION**

Application number : **95303745.4**

Int. Cl.<sup>6</sup> : **B64D 45/02**

Date of filing : **01.06.95**

Priority : **02.06.94 GB 9411006**

Date of publication of application :  
**06.12.95 Bulletin 95/49**

Designated Contracting States :  
**DE ES FR GB IT SE**

Applicant : **BRITISH AEROSPACE PUBLIC  
LIMITED COMPANY**  
**Warwick House,**  
**P.O. Box 87,**  
**Farnborough Aerospace Centre**  
**Farnborough, Hants. GU14 6YU (GB)**

Inventor : **Pridham, Barry John, British Aerosp.**  
**Def. Co. Ltd.**  
**Mil. Aircraft Div.,**  
**PO Box 87,**  
**Farnborough A. Cen.**  
**Farnborough, Hants GU14 6YU (GB)**  
Inventor : **Stephens, Austyn, Ch., Brit. Aerosp.**  
**Def. Co. Ltd.**  
**Mil. Aircraft Div.,**  
**PO Box 87,**  
**Farnborough A. Cen.**  
**Farnborough, Hants GU14 6YU (GB)**  
Inventor : **Jones, Christopher Ch., Brit. Aerosp.**  
**Def. Co. Ltd.**  
**Mil. Aircraft Div.,**  
**PO Box 87,**  
**Farnborough A. Cen.**  
**Farnborough, Hants GU14 6YU (GB)**

Representative : **Gold, Tibor Z.**  
**Stephenson Harwood**  
**One, St. Paul's Churchyard**  
**London EC4M 8SH (GB)**

**Method of fastening composite aircraft skins.**

The present invention provides a method of fastening an outer composite aircraft skin (12) to an inner substructure (14), which may be the wall of a fuel tank, and a fastener combination. The invention includes the steps of incorporating an electrically conductive layer (26) in an outer surface of the outer composite skin (12), inserting a bolt (11) through the electrically conductive layer (26) and the outer composite skin (12) and through the inner substructure (14), securing the bolt (11) by means of a nut (22) directly or indirectly engaging the inner surface of the inner substructure (14), and applying insulating material (34) over the head (16) of the bolt.

**EP 0 685 389 A1**




FIG. 1

This invention relates to aircraft lightning protection arrangements and more particularly to methods for fastening aircraft skin panels to an aircraft substructure, which may for example be the wall of a fuel tank, when the panels and substructure are made from composite materials such as carbon fibre composites.

Carbon fibre composites are being used increasingly for aircraft structures in place of the aluminium and similar metallic components formerly used. Although carbon fibre composite structures are generally stronger and stiffer than their metallic counterparts, nevertheless they lack the lightning strike tolerance of the metallic components.

A lightning strike to an aircraft causes a high electric current, which may typically be of the order of 100,000 amps, to flow through the aircraft frame. In a carbon fibre composite structure, the carbon fibre plies act as very high resistance conductors and the resin between the plies acts as highly capacitive dielectric layers so that lightning striking the carbon fibre composite results in an increasing potential difference produced across the ply structure but no readily available electrically conductive path for discharging the current. The current therefore tends to concentrate at the fasteners between the skin panels and the aircraft substructure, since the fasteners are generally made of highly conductive alloys for strength. When the lightning energy is unable to dissipate at a fast enough rate, arcing and dangerous sparks are likely to occur.

This is a considerable problem, especially when the substructure is the wall of a fuel tank and arcing carries the highly dangerous risk of injecting sparks, molten material and hot gasses into the fuel tank.

A considerable amount of research has been devoted to providing solutions to this problem but so far none has proved entirely satisfactory for purposes of practical production.

One known approach to reduce the effect of lightning strikes on non-metallic structures is to apply, by flame spraying, woven screen, foil or plating, a conductive layer such as aluminium to the outer surface of the skin panels after fastening has been completed. The fastener heads are insulated from this conductive surface layer, for example by employing a glass fibre backing for the metallic layer, which is bonded to the skin panels over the fastener heads before the application of the metallic layer. One problem with this form of protection is that a secondary bonding operation is required to bond the glass fibre backing and conductive layer to the already assembled structure and it is difficult to achieve a satisfactory bond. The protective conductive layer adds mass without contributing to the strength of the assembled structure and also is vulnerable to environmental damage and is difficult to maintain. The production and maintenance of such an arrangement is thus

clearly expensive.

Another approach is to employ various special designs of fastener, for example as disclosed in our earlier patents EP-B-0269458 and EP-B-2212580. The fasteners disclosed in these patents employ a bevelled head for countersinking into the surface of the skin panel into intimate contact therewith, and a nut for securing the fastener in place, which nut is designed to transmit electric current safely to the substructure such that arcing will not occur. Again, this approach to the problem of arcing is expensive because of the need for special designs of fastener.

The present invention seeks to overcome the problems of lightning strike in a composite aircraft structure in an efficient and relatively inexpensive fashion, which does not require the use of specially designed fasteners.

According to the present invention there is provided a method of fastening an outer composite aircraft skin to an inner substructure including the steps of incorporating an electrically conductive layer in or applying it to an outer surface of the outer composite skin, inserting a bolt through the electrically conductive layer and the outer composite skin and through the inner substructure, and securing the bolt by means of a nut directly or indirectly engaging the inner surface of the inner substructure.

According to one aspect of the present invention, there is provided a method of fastening an outer composite aircraft skin to an inner substructure including the steps of incorporating an electrically conductive layer in or applying it to an outer surface of the outer composite skin, inserting a bolt through the electrically conductive layer and outer composite skin and through the inner substructure, securing the bolt by means of a nut directly or indirectly engaging inner surface of the inner substructure, and applying insulating material over the head of the bolt.

Preferably, the electrically conductive layer is a metal strip applied along rows of fastener openings in the outer composite skin.

The insulation material may be applied in the form of an insulation strip over the outer surface of the bolt heads during the normal aircraft painting process, either before or after a primer coat. Alternatively, the bolt head may be countersunk into the outer composite skin to a depth below the level of the electrically conducting layer and the insulation material may be applied to the bolt head to be substantially flush with the outer surface of the electrically conductive layer.

The electrically conductive layer provides a conductive path to divert much of the electrical current from a lightning strike away from the fasteners, and the insulation material ensures that any arcing which does occur attaches preferentially to the electrically conductive layer rather than to the fastener and thus reduces the probability of an arc dwelling on the head of the fastener. Consequently, a substantial propor-

tion of the lightning energy is dissipated away from the fastener and the likelihood of arcing occurring within the inner substructure is minimised, which is essential in the case of the inner substructure comprising the wall of a fuel tank.

According to another aspect of the present invention, there is provided a method of fastening an outer composite aircraft skin to an inner substructure including the steps of incorporating an electrically conductive layer in or applying it to an outer surface of the outer composite skin, inserting a bolt through openings in the electrically conductive layer and the outer composite skin and in the inner substructure, wherein the bolt is an interference fit at least in the opening in the outer composite skin, and securing the bolt by means of a nut directly or indirectly engaging the inner surface of the inner substructure.

The invention also provides a fastening obtained by any of the method according to the invention mentioned above.

The invention is described further, by way of example, with reference to the accompanying drawings in which:

Figure 1 is a cross-section through a fastener installed in an aircraft structure according to the present invention;

Figure 2 is a cross-section through a fastener installed in an aircraft structure according to another embodiment of the present invention; and

Figure 3 is a cross-section through a fastener installed in an aircraft structure according to a further embodiment of the present invention.

Referring to figure 1, a fastener 10 is shown securing a skin panel 12 of an aircraft structure to an inner substructure 14 comprising the wall of a fuel tank. Both the skin panel 12 and the substructure 14 are made of carbon fibre composite material of low weight and high strength. The fastener 10 is made of metal and comprises a bolt 11 having a bevelled head 16, which is countersunk into a correspondingly shaped opening 18 in the skin panel 12, and a shank 20, which passes through the skin panel 12 and substructure 14 to be secured by a metallic nut 22 engaging the substructure 14. An insulating shim 24 is interposed between the skin panel 12 and the substructure 14 as a filler to make up for differences in the thickness of the skin panel 12.

As shown, a metallic strip 26 is formed in an outer surface of the skin panel 12 during manufacture, and the method of fastening the aircraft structure involves inserting the bolt 11 of the fastener 10 through an opening 28 in the metallic layer 26 and remainder of the skin panel 12 and through a corresponding opening 30 in the substructure 14, following which the nut 22 is applied to the shank 20 of the bolt for securing the fuel tank in place.

Subsequently, the aircraft structure is painted and the normal primer coat 32 is applied over the out-

er surface of the skin panel 12, covering the metallic strip 26 and the head 16 of the fastener 10, which is flush with the outer surface of the metallic strip 26. Next, an insulating layer 34 is applied over the primer coat 32 in the vicinity of the fastener 10 to cover the bolt head 16. Finally, the usual layer or layers 36 of paint are applied over the entire surface.

The metallic strip 26 shown here is solid and of sufficient density, ie. overall cross-sectional area to ensure a safe conductive path to divert much of the electric current, generated by lightning strikes in use, away from the fastener 10. The insulating layer 34 ensures that any arcing occurs in the vicinity of the metallic strip rather than the bolt head 16 of the fastener 10 and assists in dissipation of the lightning energy away from the fastener 10 and hence well away from the interior of the fuel tank.

A modification of the invention will now be described with reference to figure 2, in which similar reference numerals have been employed for similar parts. Only the differences will be described.

In the fastening shown in figure 2, the head 16 of the bolt 11 of the fastener 10 is countersunk into the skin panel 12 so that its outer surface 40 lies below the outer surface of the skin panel 12, i.e. below the outer surface of the metallic strip 26. In this instance, a layer of insulating material 42 is applied over the bolt head 16 within the opening 28 to fill the remainder of the opening until the insulating layer 42 is flush with the outer surface of the skin panel 12 and with the outer surface of the metallic strip 26. Subsequently, the primer coat 32 and paint layer 36 are applied in the usual way.

The effects and benefits of the fastening obtained as shown in figure 2 are similar to those obtained with the fastening shown in Figure 1.

A further modification of the invention will now be described with reference to Figure 3. Again, similar reference numerals have been employed for similar parts and only the differences will be described.

In this instance, the bolt 11 of the fastener 10 is inserted through the metallic strip 26 and the remainder of the skin panel 12 as in the case of the Figure 1 embodiment, and the outer surface of the head 16 is flush with the outer surface of the metallic strip 26. The fastener 10 is sized to be a tight, ie. interference, fit within the openings 18 and 30 in the skin panel 12 and the substructure 14 respectively so that the fastener 10 is in good conductive contact with the high resistance conductive carbon fibre plies in the composite material of the skin panel 12 and the substructure 14. Additionally, the bolt head 16 is embedded within the metallic strip 26 such that a conductive path exists from the head 16 to the metallic strip 26 for the dissipation of lightning energy.

In this embodiment, therefore, the insulating layer is omitted but the fastener 10 is in a close interference fit with the surrounding carbon fibre composite

material and can thus tolerate the high electric current generated by lightning strikes and survive without sparking. Any sparks which do arise and their products are unable to escape from within the openings 18 and 30 into the surrounding air and are thereby rendered harmless. It has been found that this embodiment is practical with certain types of fastener 10.

Various modifications are possible within the scope of the invention. For example, the fastener 10 may be any conventional fastener. In the case of the illustrated bolt 11, the bolt head 16 may be flat sided and multifaceted, or it may be frustoconical; and the nut 22 may be in direct or indirect contact with the substructure 14.

Although the metallic strip 26 is shown inset into the skin panel 12, it may alternatively be applied over the outer surface of the skin panel 12 and then the fastener 10 be inserted through both an opening in the strip 26 and an opening in the skin panel 12.

The metallic strip 26 employed in each of the described embodiment is solid but an alternative possibility is to use a strip which is substantially solid but which is pierced by occasional relatively small openings, so long as the density, or cross-sectional area, of the strip remains sufficient to establish a safe conductive path for dissipating lightning energy.

In the case of the figure 1 embodiment, the insulating layer 34 is shown applied over the primer coat 32 but it may alternatively be applied before and hence under the primer coat 32. The effects will be the same.

A plurality of the metallic strips 26 may be arranged to form an interconnecting grid extending both spanwise and chordwise of an aircraft panel to offer a larger metallic area over which lightning strike energy can be dissipated. In this instance, the grid may be connected to a metallic part of the structure to provide a route for the current to pass from the composite panel to a metallic structure of the aircraft.

## Claims

1. A method of fastening an outer composite aircraft skin (12) to an inner substructure (14) including the steps of inserting a bolt (11) through the outer composite skin and the inner substructure, and securing the bolt by means of a nut (2) directly or indirectly engaging an inner surface of the inner substructure, and characterised by incorporating an electrically conductive layer (26) in or applying it to an outer surface of the outer composite skin and, further, inserting the bolt through the electrically conductive layer as well as the outer composite skin and the inner substructure.

2. A method according to claim 1 characterised by the step of applying insulating material (34, 42)

over a head (16) of the bolt.

3. A method according to claim 2 characterised by the step of painting the outer composite skin and applying an insulation strip (34) over the outer surface of the head of the bolt during the painting step to provide the insulating material.

4. A method according to claim 3 in which the insulation strip is applied either before or after a primer coat of paint.

5. A method according to claim 2 comprising countersinking the head of the bolt into the outer composite skin to a depth below the level of the electrically conductive layer, and applying the insulating material (42) to the head of the bolt to be substantially flush with an outer surface of the electrically conductive layer.

6. A method according to any preceding claim characterised by employing a solid or substantially solid metal strip (26) to provide the electrically conductive layer.

7. A method according to any of claims 1 to 5 characterised by applying a metal strip (26) along rows of openings for respective fasteners in the outer composite skin to provide the electrically conductive layer.

8. A method according to any of claims 1 to 6 characterised by the step of inserting the bolt with an interference fit into an opening (18) in the outer composite skin.

9. A combination of an outer composite aircraft skin (12), an inner substructure (14), and a fastener (10) fixing said outer skin to said inner substructure, the fastener comprising a bolt inserted through the outer skin and the inner substructure and a nut on the bolt engaging directly or indirectly an inner surface of the inner substructure, and characterised by an electrically conductive layer (26) on the outer skin, the bolt being inserted through the electrically conductive layer as well as the outer skin and the inner substructure.

10. A combination according to claim 9 characterised by an insulating material (34, 42) over a head (16) of the bolt, and optionally characterised in that the bolt is an interference fit in an opening (18) in the outer composite skin.






FIG.2




FIG. 3






European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 95 30 3745

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	WO-A-84 01487 (THE BOEING COMPANY) * page 3, line 21 - page 4, line 2 * ---	1-5,9	B64D45/02
X	GB-A-2 201 737 (BRITISH AEROSPACE PUBLIC LIMITED COMPANY) * page 5, line 14 - page 6, line 11 * ---	1,6,7	
X	GB-A-902 268 (DOUGLAS AIRCRAFT COMPANY, INC) * page 3, line 115 - line 129 * * page 4, line 41 - line 55; figure 3 * ---	1,6	
A	EP-A-0 371 905 (UNITED TECHNOLOGIES) * column 2, line 25 - column 3, line 21 * ---	1	
A	US-A-3 755 713 (PASZKOWSKY) * the whole document * ---	1	
A	US-A-4 628 402 (COVEY) * the whole document * -----	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			B64D
Place of search		Date of completion of the search	Examiner
THE HAGUE		10 August 1995	Hauglustaine, H
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone  V : particularly relevant if combined with another document of the same category  A : technological background  O : non-written disclosure  P : intermediate document</p> <p>T : theory or principle underlying the invention  E : earlier patent document, but published on, or after the filing date  D : document cited in the application  L : document cited for other reasons  &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)



**THIS PAGE BLANK (USPTO)**